

Shrieve Product Specification

ZEROL RFL 46-EP

Sales Specification



Version No: 003

Date: 15-11-2016

Characteristic	Method	Unit	Specification	
			Lower Tolerance	Upper Tolerance
Viscosity (40°C)	ASTM D445	mm ² /s	42.0	48.0
Colour	ASTM D1544	Gardner		1.0
Water	ASTM E203	wt%		0.05
Suspended Material	ASTM E284		Substantially Free	
Appearance (20°C)	ASTM E284		Clear to Slightly Hazy	
Pour Point	ASTM D97	°C		-40
Capping Efficiency	ASTM E326	%	85.0	100

The Americas	Europe, Middle East & Africa	Asia Pacific
Shrieve Chemical Products Inc., 1755 Woodstead Court The Woodlands Texas 77380-1448 United States of America Tel: Toll free within US: (800) 367 4226 Tel: +1 281 367 4226 Fax: +1 281 367 0071	Shrieve Products International Ltd Suite 39, 40 Churchill Square Kings Hill West Malling Kent, ME19 4YU United Kingdom Tel: +44 1732 520600 Fax: +44 1732 520601	Shrieve Chemical (Shanghai) Ltd Room 301, Block 2 Juxin information Technology Park 188 Pingfu Road, Xuhui district Shanghai 200231 Peoples Republic of China Tel: +86 21 63598215/6/7 Fax: +86 21 63524607
www.shrieve.com		